



G-PAEK™ 1220GF

Product Details: Ultra high performance thermoplastic polymer, 20% glass fiber reinforced in Polyether Ketone, semi-crystalline granules suitable for injection molding, easy flow, Dark Beige in color and also custom colors in Blue and Black.

Application Areas: Suitable for high temperature applications, where higher strength in load-bearing applications. Chemically resistant to aggressive environments, suitable for sterilization for medical and food contact applications.

Typical Properties:

PROPERTY	TEST METHOD/CONDITIONS	UNIT	G-PAEK™ 1220GF
General Properties			
Density	23°C	g/cc	1.45
Water Absorption	ASTM D 570-98	%	0.05
Rockwell Hardness	ASTM D 785/M Scale		100
Shore D Hardness	ASTM D 2240-05		91
Mold Shrinkage (410°C nozzle, 220°C Mold)	Along Flow	%	0.6
	Across Flow	%	0.9

Thermal Properties			
Glass Transition Temperature(Tg)	ASTM D 3418	°C	152
Melting Point (Tm)	ASTM D 3418	°C	372
Continuous Use Temperature (Expected)	UL 746B	°C	280

Mechanical Properties at 23°C			
Tensile Strength	ASTM D 638	MPa	130
Tensile Modulus	ASTM D 638	GPa	8.5
Elongation at Break	ASTM D 638	%	2.8
Flexural Strength	ASTM D 790	MPa	192
Flexural Modulus	ASTM D 790	MPa	8.6
Izod Impact Strength(Notched)	ASTM D 256	J/m	45
Izod Impact Strength(Un-notched)	ASTM D 256	J/m	680



PROPERTY	TEST METHOD/CONDITIONS	UNIT	G-PAEK™ 1220GF
Fire Properties			
Flammability	UL 94/0.8 mm	-	V-0

Recommended Processing Conditions	
Drying Temperature/Time	4-6 hrs at 150°C
Temperature Settings	390-420°C
Nozzle Temperature	420°C
Hopper/ Throat Temperature	60-80°C
Mold Temperature	200-220°C

Nominal Granule Size	
<ul style="list-style-type: none"> • Dimensions, length 2.0 – 4.0 mm, diameter 2.0 – 3.5 mm • No longs greater than 8.0 mm • Granules of uniform cut and color 	

THE INFORMATION PROVIDED IN THIS DATA SHEET CORRESPONDS TO OUR KNOWLEDGE ON THE SUBJECT AT THE DATE OF ITS PUBLICATION. THIS INFORMATION MAY BE SUBJECT TO REVISION AS NEW KNOWLEDGE AND EXPERIENCE BECOMES AVAILABLE. THE DATA PROVIDED FALL WITHIN THE NORMAL RANGE OF PRODUCT PROPERTIES AND RELATE ONLY TO THE SPECIFIC MATERIAL DESIGNATED; THESE DATA MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS, ADDITIVES OR PIGMENTS OR IN ANY PROCESS, UNLESS EXPRESSLY INDICATED OTHERWISE. THE DATA PROVIDED SHOULD NOT BE USED TO ESTABLISH SPECIFICATION LIMITS OR USED ALONE AS THE BASIS OF DESIGN; THEY ARE NOT INTENDED TO SUBSTITUTE FOR ANY TESTING YOU MAY NEED TO CONDUCT TO DETERMINE FOR YOURSELF THE SUITABILITY OF A SPECIFIC MATERIAL FOR YOUR PARTICULAR PURPOSES. SINCE GHARDA PLASTICS CANNOT ANTICIPATE ALL VARIATIONS IN ACTUAL END-USE CONDITIONS GHARDA PLASTICS MAKES NO WARRANTIES AND ASSUMES NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION. NOTHING IN THIS PUBLICATION IS TO BE CONSIDERED AS A LICENSE TO OPERATE UNDER OR A RECOMMENDATION TO INFRINGE ANY PATENT RIGHTS. GHARDA PLASTICS ADVISES YOU TO SEEK INDEPENDENT COUNSEL FOR A FREEDOM TO PRACTICE OPINION ON THE INTENDED APPLICATION OR END-USE OF OUR PRODUCTS. FOR FURTHER INFORMATION, PLEASE CONTACT YOUR GHARDA PLASTICS REPRESENTATIVE