



# G-PAEK™ 1120FEP

**Product Details:** Ultra High Performance Thermoplastic polymer, 20% PTFE blended in Polyether Ketone, semi-crystalline fine powder suitable for compression molding, milky white in color.

**Application Areas:** Suitable for high temperature applications, where higher strength & less coefficient of Friction in load-bearing applications. e.g. Valve Seat & Mechanical Seal is required. Chemically resistant to aggressive environments, suitable for valve sheet application in ball valves.

**Typical Properties:**

PROPERTY	TEST METHOD/CONDITIONS	UNIT	G-PAEK™ 1120FEP
<b>General Properties</b>			
Bulk Density	ASTM D 1895B	g/cc	0.3

<b>Particle Size Distribution</b>
D(50)<10 micron & D(0.99) <100 micron

<b>Thermal Properties</b>			
Glass Transition Temperature(Tg)	ASTM D 3418	°C	152
Melting Point (Tm)	ASTM D 3418	°C	372
Continuous Use Temperature (Expected)	UL 746B	°C	280

<b>Rheological Properties</b>			
Melt Viscosity at 400°C	ASTM D 3835/@1000 s <sup>-1</sup>	Pa.s	300-350

<b>Fire Properties</b>			
Flammability	UL 94/0.8 mm		V-0

THE INFORMATION PROVIDED IN THIS DATA SHEET CORRESPONDS TO OUR KNOWLEDGE ON THE SUBJECT AT THE DATE OF ITS PUBLICATION. THIS INFORMATION MAY BE SUBJECT TO REVISION AS NEW KNOWLEDGE AND EXPERIENCE BECOMES AVAILABLE. THE DATA PROVIDED FALL WITHIN THE NORMAL RANGE OF PRODUCT PROPERTIES AND RELATE ONLY TO THE SPECIFIC MATERIAL DESIGNATED; THESE DATA MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS, ADDITIVES OR PIGMENTS OR IN ANY PROCESS, UNLESS EXPRESSLY INDICATED OTHERWISE. THE DATA PROVIDED SHOULD NOT BE USED TO ESTABLISH SPECIFICATION LIMITS OR USED ALONE AS THE BASIS OF DESIGN; THEY ARE NOT INTENDED TO SUBSTITUTE FOR ANY TESTING YOU MAY NEED TO CONDUCT TO DETERMINE FOR YOURSELF THE SUITABILITY OF A SPECIFIC MATERIAL FOR YOUR PARTICULAR PURPOSES. SINCE GHARDA PLASTICS CANNOT ANTICIPATE ALL VARIATIONS IN ACTUAL END-USE CONDITIONS GHARDA PLASTICS MAKES NO WARRANTIES AND ASSUMES NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION. NOTHING IN THIS PUBLICATION IS TO BE CONSIDERED AS A LICENSE TO OPERATE UNDER OR A RECOMMENDATION TO INFRINGE ANY PATENT RIGHTS. GHARDA PLASTICS ADVISES YOU TO SEEK INDEPENDENT COUNSEL FOR A FREEDOM TO PRACTICE OPINION ON THE INTENDED APPLICATION OR END-USE OF OUR PRODUCTS. FOR FURTHER INFORMATION, PLEASE CONTACT YOUR GHARDA PLASTICS REPRESENTATIVE